

GEODREN PEIT 209



Nonwoven geotextile made by polyester, needlepunched and calandered, produced without using of any glues or chemical binders and post-consumer raw material.

Physical properties	Standard		Value	Units	Tolerance %	Tolerance (units)
Mass per unit area	[EN ISO 9864]		200	g/m ²	+/- 10	+/- 20
Thickness	[EN ISO 9863-1]	2 kPa	0,80	mm	+/- 20	+/- 0,16
Mechanical properties	Standard		Value	Units	Tolerance %	Tolerance (units)
Tensile strength	[EN ISO 10319]	MD	2,5	kN/m	- 15	- 0,4
	[EN ISO 10319]	CMD	2,5	kN/m	- 15	- 0,4
Elongation at maximum load	[EN ISO 10319]	MD	30	%	+/- 30	+/- 9
	[EN ISO 10319]	CMD	50	%	+/- 30	+/- 15
Static puncture resistance (CBR)	[EN ISO 12236]		0,40	kN	- 30	- 0,12
Dynamic puncture resistance	[EN ISO 13433]		38	mm	+ 20	+ 8
Hydraulic properties	Standard		Value	Units	Tolerance %	Tolerance (units)
Velocity index	[EN ISO 11058]		70	mm/s	- 30	- 21
Characteristic opening size	[EN ISO 12956]		60	µm	+/- 30	+/- 18
Durability properties						
Weathering resistance	[-]	To be covered within 1 day from the day of installation.				
Service life		Forecast minimum durability of 5 years in natural ground with 4<pH<9 and soil temperature < 25°C.				

The values given are an average obtained in our laboratories and in official testing institutes.
The confidence level is 95%
The right is reserved to make changes any time without notice.

MD = Machine Direction/Longitudinale; CMD = Cross Machine Direction/Trasversale; NA = Not Applicable/Non Applicabile

Ref.
Cod. 001146 Rev.1 Data Rev.: 07-04-2013

Approved by CQ


Approved by UT
